



## SUN PROCESS Product Information Data

### 990-50 BLEACHED KRAFT SILICONE RELEASE SEPARATORS

*Thickness ± 10%, including adhesive  
The following characteristics are on typical laboratory data:*

<u>Property</u>	<u>Typical Value</u>	<u>Control Limit</u>
<b>Basis Weight</b> (24 x 36/500)	50	42 to 70
<b>Caliper</b> (Mils)	3	2.5 to 4
<b>Yield</b> (Sq. inches/lb.)	8640	10285 to 6171
<b>Apparent Density</b> (Pound per ream per Mil)	16.33	14 to 17.5
<b>*Release Side 1</b> (Grams)	40	20 to 60
<b>Side 2</b>	40	20 to 60
<b>*Initial Keil Test</b> Modified version of TAPPI useful method (UM) 502		

ISO 9001:2015

*This Sun Process product was manufactured under our quality system registered to ISO 9001:2015 standards*

#### TECHNICAL INFORMATION

*The technical information, recommendations and other statements contained in this document are based upon tests or experience that Sun Process believes are reliable, but the accuracy or completeness of such information is not guaranteed. They do not relieve the purchaser from the responsibility of examining the products upon delivery or provide assurance of the products suitability for a particular purpose.*

*Suitability for any given application is the sole responsibility of the user.*

#### SUN PROCESS CONVERTING, INC.

1660 Kenneth Drive, Mt. Prospect, IL 60056

Toll Free: (800) 323-0697 • In Illinois: (847) 593-0447 • Fax: (847) 593-0115

Website: [www.sunprocess.com](http://www.sunprocess.com) • Email: [sales@sunprocess.com](mailto:sales@sunprocess.com)